



Flexane® Brushable

Description: A tough, rubber-like urethane compound for making a broad range of repairs to protect against wear, abrasion, and noise reduction.

Intended Use: Protect equipment surfaces from wear and abrasion.
Protect processing equipment such as coating hoppers, lining chutes, pump volutes, impellers, and fan housings.

Product features:
Bonds with primers to metal, concrete, rubber, wood, and fiberglass
Excellent tear resistance
Mixes easily
Coats up to 50 mils in one pass
Highly resistant to impact and abrasion

Limitations: Keep from freezing. The resin may crystallize at temperatures below 50°F. This does not affect the properties of the product. If after opening, resin has an opaque, whitish color, apply lid and allow can to stand at 70°F overnight or until resin becomes clear.

Typical Physical Properties: *Technical data should be considered representative or typical only and should not be used for specification purposes.*

Cured 7 days @ 75° F

Abrasion Resistance	90 mg loss per 1,000 revolut
Color	Black
Coverage/lb	3.6 sq. ft. @ 50 mil
Cure Time	24 hours
Cured Hardness	86A
Cured Shrinkage	0.23 in./in.
Dielectric Strength	340 volts/mils
Functional Cure	18 hours
Maximum Elongation	600%
Maximum Operating Temperature	Dry: 180°F; Wet: 120°F
Mix Ratio	80 resin:20curing agent / wt
Mixed Viscosity	40,000 cps
Percent Solids by Volume	77
Pot Life	45 min. @ 75°F
Specific Volume	26 in.(3)/lb.
Tear Resistance	400 pli
Tensile Strength	3,500 psi

TESTS CONDUCTED

Cured Hardness Shore D ASTM D 2240
Dielectric Constant ASTM D 150
Maximum Elongation ASTM D 412
Cure Shrinkage ASTM D 2566
Tensile Strength (Urethanes) ASTM D 412
Tear Resistance ASTM D 624

Surface Preparation: For METAL SURFACES, thoroughly clean area to be repaired, rebuilt, or lined with Devcon® Cleaner Blend 300. Remove any oil, grease, or dirt. Roughen surface by grinding with a coarse wheel or an abrasive disc pad. To prime this surface, apply a coat of Devcon FL-10 Primer and allow to dry tack-free for 5-15 minutes. If the metal surface requires maximum tear resistance or is exposed to moisture, or if submerged in water, use Devcon® FL-10 and Devcon® FL-20 Primer.

For RUBBER SURFACES, thoroughly clean area with an abrasive pad and Devcon® Cleaner Blend 300. Surface can also be roughened with a grinding wheel so that it is coarse and free from oil and dirt that may clog the "pores" of the rubber. Wipe or roughen surface with Cleaner Blend 300 until the cloth no longer picks up the color of the rubber. The rubber should appear new or deeper in color. To prime this surface, apply a coat of Devcon® FL-20 Primer and allow to dry tack-free for 15-20 minutes. Use Devcon®FL-40 Primer on "hard-to-bond" rubber surfaces as this gives ultimate peel resistance. Multiple coats may be necessary for porous rubber surfaces.

For MAXIMUM ADHESION, sandblast the surface with an angular abrasive until a minimum depth profile of 2-3 mils is met. Blast to near-white finish specification SSPC-SP5 (Steel Structure Painting Council). Prime surface immediately after sandblasting to prevent oxidation.

Mixing Instructions: ---- To ensure proper cure speeds and hardness, mix Flexane at a temperature between 65°F-85°F. ----
FOR 1 LB. UNITS

1. Add hardener to resin.
2. Vigorously mix with screwdriver or spatula for two minutes, while continuously scraping material away from sides and bottom of container.
3. Transfer the mixed material to the plastic container (included in kit).
4. Wipe spatula clean, and stir again for two more minutes.

FOR 400ML CARTRIDGES:

1. Attach mix nozzle to cartridge
2. Follow application instructions; no mixing is required.

FOR 10LB. UNITS:

Use a propeller-type Jiffy Mixer Model ES on an electric drill.

Mix until color is uniform and consistent (approx 4-6 min.).

NOTE: Completely submerge propeller, otherwise large amounts of air will be added resulting in air bubbles on the finished product's surface.

Application Instructions:

---- FOR MAXIMUM ADHESION, apply a suitable Devcon primer to all substrates prior to application. ----

Metals	FL-10 Primer (2 coats)
Rubber	FL-20 Primer
Wood	FL-20 Primer
Fiberglass	FL-20 Primer
Concrete	FL-20 Primer
Rigid Plastics	FL-20 Primer

1. Brush a thin coat of Flexane over the substrate, then pour from one side of the mold to the other side, so as to evacuate any air as the Flexane fills the area.
2. Gently blow hot air over the finished surface to ensure a perfect mold with no blow holes or air entrapment. Use a hot air gun and gently wave over the surface to break all the air bubbles.
3. Allow to cure six (6) hours before returning equipment to light service. The repair may then be ground flush using a 24 or 36 grit sanding disc. Do not overheat the work surface. Full cure takes seven (7) days @ 70°F.

ADDITIONAL INFORMATION

Flexane Accelerator is used to increase Flexane's cure speed at temperatures as low as 32°F. One-half tsp. (2 gms) of Accelerator reduces the cure time of 1 lb. of Flexane by 50%. Use 2 tsp. or less of Accelerator for each 1 lb. of Flexane. See Flexane Accelerator TDS for further information.

Storage:

Store at room temperature, 70 °F.

Compliances:

None

Chemical Resistance:

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F

1,1,1-Trichloroethane	Poor	Potassium Hydroxide 40%	Very good
Aluminum Sulfate 10%	Very good	Sodium Hydroxide 50%	Very good
Cutting Oil	Fair	Sulfuric 50%	Fair
Hydrochloric 10%	Fair	Xylene	Poor
Isopropanol	Poor		
Methyl Ethyl Ketone	Poor		
Phosphoric 10%	Fair		
Phosphoric 50%	Fair		

Precautions:

Please refer to the appropriate safety data sheet (SDS) prior to using this product.

For technical assistance, please call 1-855-489-7262

FOR INDUSTRIAL USE ONLY

Warranty:

ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer:

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Performance Polymers makes no representations or warranties of any kind concerning this data.

Order Information:

15350 1 lb. kit