



Silite RTV®

Description: A Silicone adhesive/sealant compound for sealing, caulking, bonding, and making gaskets.

Intended Use: Weather-proofing electrical components, caulking plumbing fixtures, sealing glass, and making form-in-place gaskets.

Product features: Flexible from -60°F to 450°F (white & clear)
Moisture curing
Flexible from -60°F to 500°F/ 600°F intermittent (Red)
Resistant to weather and chemicals

Limitations: None

Technical data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties:	Cured 7 days @ 75° F		TESTS CONDUCTED
	Cured hardness	30 Shore A	Dielectric Constant ASTM D 150 Maximum Elongation ASTM D 412 Tensile Strength (Urethanes) ASTM D 412 Dielectric Strength, volts/mil ASTM D 149 Tear Resistance ASTM D 624 Volume Resistivity , ohm/cm ASTM D 149
	Uncured		
	Color	Clear, White, or Red	
	Coverage/lb	100 linear ft.	
	Density	1.05 gm/cm(3)	
	Dielectric Constant	2.8	
	Dielectric Strength	375 volts/mils	
	Elongation	600%	
	Tangent Loss	10(3)	
	Tear Resistance	47 pli	
	Tensile Strength	400 psi	
	Viscosity	Non-sag gel up to 3/4"	
	Viscosity	300,000 - 400,000	
	Volume Resistivity	7x10(13) ohm/cm	

Surface Preparation: Clean surface by solvent-wiping any deposits of heavy grease, oil, dirt, or other contaminants. Surface can also be cleaned with industrial cleaning equipment such as vapor phase degreasers or hot aqueous baths.

Mixing Instructions: Mixing is not applicable to this product.

Application Instructions: Clip tip of cartridge back to desired thickness. Drop into the caulking gun and squeeze trigger.

Storage: Store at room temperature, 70 °F.

Compliances: Meets USDA, FDA 177.2600. Meets MIL-A-46106A Group 1, Type 1, NSF ANSI 51

**Chemical
Resistance:**

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F

Ammonia	Fair
Ammonium Hydroxide 20%	Very good
Cutting Oil	Very good
Ethanol	Excellent
Gasoline (Unleaded)	Poor
Glycols/Antifreeze	Very good
Hydrochloric 10%	Poor
Hydrochloric 36%	Poor

Methanol	Fair
Motor Oil	Poor
Nitric 50%	Fair
Potassium Hydroxide 20%	Excellent
Sodium Hydroxide 10%	Excellent
Sodium Hydroxide 50%	Excellent
Sodium Hypochlorite	Very good
Sulfuric 10%	Very good

Precautions:

Please refer to the appropriate safety data sheet (SDS) prior to using this product.

For technical assistance, please call 1-855-489-7262

FOR INDUSTRIAL USE ONLY

Warranty:

ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer:

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Performance Polymers makes no representations or warranties of any kind concerning this data.

**Order
Information:**

17100 Clear3 oz.
17140 White10.3 fl oz.
17130 Red 10.3 fl oz.
17150 Clear10.3 fl oz.