



# Permatex® Zip Grip® TE 1000

**Description:** A medium-viscosity, rubber-toughened instant adhesive with exceptional impact resistance.

**Intended Use:** Bond wood, cork, leather, rubber to metal weatherstripping, audio speakers, PCB wire tacking

**Product features:**

- Bonds dissimilar substrates
- Exceptional thermal shock performance
- High impact resistance
- Toughened Ethyl Medium Viscosity [Clear]
- Enhanced toughness to peel and shock loads
- Humidity and water resistant
- Permanent
- Temperature-resistant to 280°F

**Limitations:** Not recommended for use on glass due to substrate weakness

**Typical Physical Properties:** *Technical data should be considered representative or typical only and should not be used for specification purposes.*

**Cured 7 days @ 75° F**

<b>Adhesive Tensile Shear</b>	<b>3,700 psi</b>
<b>Coefficient of Thermal Expansion</b>	<b>.00012 in./in./°F</b>
<b>Dielectric Constant</b>	<b>5.4 @ 1KHz</b>
<b>Dielectric Strength</b>	<b>295 volts/mil @ 1KHz</b>
<b>Flashpoint</b>	<b>185°F</b>
<b>Impact Resistance</b>	<b>8 ft.lb./in.(2)</b>
<b>Melting Point</b>	<b>329°F</b>
<b>Peel Strength</b>	<b>10 pli</b>
<b>Refractive Index</b>	<b>1.49</b>
<b>Service Temperature Range</b>	<b>-65° to 280°F</b>
<b>Solubility</b>	<b>Nitromethane, Acetone</b>
<b>Volume Resistivity</b>	<b>5.3E-14 ohm/cm</b>

**TESTS CONDUCTED**

Coef. of Thermal Expansion ASTM D 696  
 Dielectric Strength, volts/mil ASTM D 149  
 Adhesive Tensile Shear ASTM D 1002  
 Dielectric Constant ASTM D 150  
 Volume Resistivity , ohm/cm ASTM D 149

**Uncured**

<b>Base</b>	<b>Ethyl cyanoacrylate</b>
<b>Color</b>	<b>Colorless liquid</b>
<b>Cure Speed</b>	<b>25-40 sec.(Steel); 25-50 sec.Plastics); 20-50 sec.</b>
<b>Full Cure</b>	<b>24 hrs.</b>
<b>Functional Cure (80%)</b>	<b>60 min.</b>
<b>Gap Filling</b>	<b>0.008"</b>
<b>Military Specification</b>	<b>MIL-A--46050C Type II Class 3</b>
<b>Shelf Life</b>	<b>1 year</b>
<b>Specific Gravity</b>	<b>1.06 g/cc</b>
<b>Viscosity</b>	<b>1,000 cps</b>

**Surface Preparation:** Clean surface by solvent-wiping any deposits of heavy grease, oil, dirt, or other contaminants. Surface can also be cleaned with industrial cleaning equipment such as vapor phase degreasers or hot aqueous baths.

---- CLEANING METHODS ----

**STEEL:**  
 Vapor degrease or cold-solvent clean (Sand blasting or other preparation is not typically required).

**ALUMINUM:**  
 Abrade with Scotch-Brite™ abrasive pads or steel wool, then clean with solvent.

**RUBBER:**  
 Wipe clean with isopropyl alcohol or solvent.

**PLASTICS:**  
Lightly abrade shiny, smooth surfaces, then solvent-wipe with suitable solvent such as 1,1,1-trichloroethane, acetone, or VM&P naphtha. Non-shiny surfaces need only be solvent-wiped.

**Mixing Instructions:** Mixing is not applicable to this product.

**Application Instructions:**

1. Apply adhesive directly from bottle [approx .006 gms per sq. in is sufficient]
2. Press surfaces together
3. Hold tightly for a few seconds

**ADDITIONAL PRODUCT INFORMATION**  
- Cyanoacrylates fixture in a few seconds on most smooth, close fitting substrates  
- They cure best at room temperature [72°F]  
- Heat does NOT accelerate the cure of cyanoacrylates  
- The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed.

**Storage:** Store in a cool, dry place.

**Compliances:** CID A-A-3097, Type II Class 3

**Chemical Resistance:** *Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F*

1,1,1-Trichloroethane	Excellent
Gasoline (Unleaded)	Excellent
Hydrochloric 10%	Poor
Motor Oil	Excellent
Sodium Hydroxide 10%	Poor

**Precautions:** Please refer to the appropriate safety data sheet (SDS) prior to using this product.

**For technical assistance, please call 1-855-489-7262**

**FOR INDUSTRIAL USE ONLY**

**Warranty:** ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

**Disclaimer:** All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Performance Polymers makes no representations or warranties of any kind concerning this data.

**Order Information:** 72161 1 lb. kit