



ITWPRC 100 NON-SHRINK – TECHNICAL BULLETIN #6251 HIGH PERFORMANCE, NON-SHRINK CEMENT GROUT

Revised: 05/2018

PRODUCT DESCRIPTION

ITWPRC 100 NON-SHRINK CEMENT GROUT is a high performance, non-shrink, precision grout that meets or exceeds all requirements of the Corps of Engineers CRD C-621 and ASTM C-1107. It is designed for a wide range of consistencies from damp pack to high fluidity, meeting the most demanding job conditions.

USE & BENEFITS

ITWPRC 100 NON-SHRINK CEMENT GROUT is recommended for grouting of anchor bolts, baseplates, structural steel and pre-cast columns, dowels, etc. which require non-shrink, high tolerance, high strength performance. It is flowable for easy placement, adheres well to concrete or steel, and exhibits good impact and vibration characteristics.

DESIGN CONSIDERATIONS

Pre-washed graded 3/8" pea gravel may be used in applications thicker than 2". In depths from 2" to 5", add 25% of the 3/8" pea gravel by weight. For depths 5" and deeper, add 50% 3/8" pea gravel by wt. When grouting in hot weather, provide shade around the area to be grouted. Use cool mixing water and protect the grout from the sun for up to 48 hours.

When grouting in cold weather, raise the temperature of the area to be grouted. Preheat the mixing water and cover the grout to retain warmth. **DO NOT** place at temperatures below 40°F or if the temperature is expected to fall below 40°F within the next 24 hour period.

ITWPRC 100 NON-SHRINK CEMENT GROUT should be kept in a shaded, dry area. At no time should the packaged material be exposed to moisture.

APPLICATION INSTRUCTIONS

Remove all dirt, oil or loose foreign material from any steel surface to come in contact with CHOCKCRETE. Concrete surfaces must be sound and roughened to insure proper bonding. Concrete surfaces should be saturated for a minimum of 4 hours but preferably for 24 hours prior to placing the grout. Remove all excess water from the foundation prior to placing ITWPRC 100 NON-SHRINK CEMENT GROUT.

Build the forms at least 1" higher than the bottom of the item being grouted.

A portable mortar mixer should be used when mixing the grout. Start with the minimum water requirements. **ADD WATER TO MIXER FIRST**, then slowly add powder.

CAUTION: DO NOT OVER WATER. Adding more water than recommended can cause bleeding, separation and a reduction of ultimate strength. **DO NOT** re-temper or add additional cement, sand or admixtures without first contacting ITW Performance Polymers.

The grout should be placed continuously by pouring from one side to the other to avoid air entrapment. Cover with clean wet rags and keep moist until final set.

Add additional water as required for desired consistency.
Water requirements per 50 lb. bag are:

PLASTIC	FLOWABLE	FLUID
6.80 to 7.00 pints water	7 to 8 pints water	8.00 to 9.25 pints water
0.85 to 0.88 gal.	0.88 to 0.94 gal	1.00 to 1.19 gal.
7.05 to 7.30 lbs.	7.30 to 7.80 lbs.	8.33 to 9.50 lbs.
3.18 to 3.29 liters	3.29 to 3.79 liters	3.79 to 4.40 liters

PHYSICAL PROPERTIES

	(PSI)	PLASTIC	FLOWABLE	FLUID	
COMPRESSIVE STRENGTH	3 days	5,900	5,400	4,800	ASTM C-109
	7 days	8,900	7,700	6,200	
	28 days	11,500	8,400	7,700	
STATIC MODULUS OF ELASTICITY	3 days 2.64 x 10 ⁶ psi 7 days 2.79 x 10 ⁶ psi 28 days 3.00 x 10 ⁶ psi				ASTM C-469
EXPANSION PERCENTAGE	3 days	0.07%	0.03%	0.02%	CRD D-621
	14 days	0.07%	0.03%	0.02%	
	28 days	0.07%	0.03%	0.02%	
COEFFICIENT OF THERMAL EXPANSION	4.76 x 10 ⁻⁶ in/in °F				ASTM C-531
FLEXURAL STRENGTH	3 days 1,055 psi 7 days 1,230 psi 28 days 1,430 psi				ASTM C-78
	3 days 550 psi 7 days 680 psi 28 days 750 psi				ASTM D-496
STRENGTH OF ANCHORS 1-1/4" dia. bolt in a 2-1/2" dia. hole with 9" embedment 1/2" dia. bolt in a 1-1/8" dia. hole with 4" embedment	TENSILE STRENGTH 53,200 lbs. 7,100 lbs.	SHEAR STRENGTH 24,300 lbs. 2,000 lbs.			ASTM E-488

PRODUCT INFORMATION

UNIT PACKAGING	Individual Bags - Super Sack			
UNIT WEIGHT	22.7 kg (50 lbs.) Bags; 1,361 kg (3,000 lb) Super Sack			
UNIT YIELD	PLASTIC Approx. 0.43 ft. ³	FLOWABLE 0.44 ft. ³	FLUID 0.45 ft. ³	
APPLICATION TEMPERATURE	45°F Minimum - 90°F Maximum			
SET TIME (APPROXIMATE)	PLASTIC Initial: 3.5 hrs Final: 4.75 hrs	FLOWABLE 4 hrs 4.8 hrs	FLUID 3.6 hrs 4.75 hrs	ASTM C-266
SHELF LIFE	1 year in dry, shaded storage			
CLEAN UP	Water			

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support. **Warranty:** ITW Performance Polymers, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment. **Warranty Claims:** If any product fails to meet the above, ITW Performance Polymers will, at its option, either replace the product or refund the purchase price. ITW Performance Polymers will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered. **Disclaimer:** ITW Performance Polymers makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose. Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Performance Polymers' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Performance Polymers' election. Under no circumstances shall ITW Performance Polymers be liable for any indirect, incidental or consequential damages. **Modification of Warranty:** No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Performance Polymers. No term of any purchase order shall serve to modify any provision of this document. **Mediation and Arbitration:** If any dispute arises relating to products or product warranties, either the purchaser or ITW Performance Polymers may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.

ITW PERFORMANCE POLYMERS

130 Commerce Drive | Montgomeryville | PA 18936 | USA | T: 215-855-8450 | E-mail: customerservice.na@itwpp.com | www.itwperformancepolymers.com