



SUPER CERAMIC REPAIR PUTTY – TECHNICAL BULLETIN #821G REPAIR PUTTY

Revised: 05/2018

PRODUCT DESCRIPTION

SUPER CERAMIC Repair Putty is a smooth ceramic-filled epoxy putty with exceptional wear resistance. The "no-slump" nature of SUPER CERAMIC Repair Putty makes it ideal for repairing overhead, vertical or curved surfaces.

USE & BENEFITS

SUPER CERAMIC Repair Putty is well suited for the repair of "severe service" pump equipment commonly found in industries, such as pulp and paper mills, chemical processing, refineries, marine and coal mining operations as well as many others.

SURFACE PREPARATIONS

The repair area should be free of all grease, dirt and oxidation. The surface should be sandblasted to "near white" metal using an 8 to 40 mesh grit. Grinding is suitable for small areas or when other methods are prohibited. The entire area should then be washed down with IMPAX IXT-59 Safety Solvent.

NOTE: Be careful not to touch the repair area with bare hands after solvent washing. SUPER CERAMIC Repair Putty should be applied as soon as possible after blasting to prevent oxidation.

APPLICATION INSTRUCTIONS

SUPER CERAMIC Repair Putty's consistency was designed to provide a stiff mix to insure its "no-slump" capabilities when applied to overhead, vertical or curved surfaces.

Place 7 parts resin and 1 part hardener by weight or 4.3 parts resin and 1 part hardener by volume on a clean, flat surface and mix thoroughly with a trowel or wide blade tool. Material should have a streakfree gray color.

NOTE: Do not mix more than 4 minutes or "no-slump" properties may diminish. Do NOT power mix.

When repairing a pump casing, the entire housing should have approximately 3mm (1/8") of SUPER CERAMIC Repair Putty applied to it. Be sure to allow adequate clearance between housing and impeller. If it is not possible to coat the entire housing, do not feather edge the SUPER CERAMIC. Instead, square off the repair area to leave at least a 3mm (1/8") application of SUPER CERAMIC Repair Putty at the edge of the damaged area.

NOTE: Do not mix more material than can be applied in 20 minutes.

Top coating SUPER CERAMIC Repair Putty with additional layers must be accomplished prior to the first layer taking a hard set - 4 hrs. @ 22°C (72°F). Once SUPER CERAMIC Repair Putty hardens, the surface must be brush blasted or abraded to insure inter-layer bonding of subsequent layers.

PHYSICAL PROPERTIES

COMPRESSIVE STRENGTH	877.5 kp/cm ² (12,700 psi)	ASTM D-695
COEFFICIENT OF LINEAR THERMAL EXPANSION	44.6 x 10 ⁻⁶ /°C 24.8 x 10 ⁻⁶ /°F	ASTM D-698
TENSILE SHEAR STRENGTH	125.4 kp/cm ² (1,800 psi)	ASTM D-1002
HARDNESS	Shore D = 90	ASTM D-1706
IZOD IMPACT STRENGTH	0.28 foot pounds/inch notch	ASTM D-256
SERVICE TEMPERATURE	-73°C to 260°C (-100°F to 500°F)	

PRODUCT INFORMATION

COLOR	Resin – Gray, Hardener – White, Gray after mixing
MIX RATIO	7 to 1 by weight 4.3 to 1 by volume
COVERAGE	280 cc (17 cu.in.)
APPLICATION TEMPERATURE	13°C (55°F) to 35°C (95°F)
CURE TIME (APPROXIMATE)	24 hours @ 22°C (72°F)
POT LIFE	20 minutes @ 22°C (72°F)
CLEAN UP	IMPAX IXT-59 Solvent or similar
APPLICATION TEMPERATURE	13°C (55°F) to 35°C (95°F)
UNIT PACKAGING	Resin (NH): 227 cc (7.7 oz) in a 12 oz plastic jar Hardener (NH): 53 cc (1.8 oz) in a 4 oz plastic jar
UNIT WEIGHT (1 LB KIT)	Resin: 405 g (0.89 lbs) Hardener: 60 g (0.13 lbs)

REFERENCE

For detailed information on the repair of eroded Kort nozzles, refer to SUPER PRODUCTS Repair Procedure #831. For detailed information on other repairs, contact ITW Performance Polymers.

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support. **Warranty:** ITW Performance Polymers, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment. **Warranty Claims:** If any product fails to meet the above, ITW Performance Polymers will, at its option, either replace the product or refund the purchase price. ITW Performance Polymers will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered. **Disclaimer:** ITW Performance Polymers makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose. Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Performance Polymers' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Performance Polymers' election. Under no circumstances shall ITW Performance Polymers be liable for any indirect, incidental or consequential damages. **Modification of Warranty:** No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Performance Polymers. No term of any purchase order shall serve to modify any provision of this document. **Mediation and Arbitration:** If any dispute arises relating to products or product warranties, either the purchaser or ITW Performance Polymers may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.

ITW PERFORMANCE POLYMERS

130 Commerce Drive | Montgomeryville | PA 18936 | USA | T: 215-855-8450 | E-mail: customerservice.na@itwpp.com | www.itwperformancepolymers.com