



Flexane® Fast Cure Rubber Repair Liquid

Description: A fast-curing, trowelable liquid urethane for repairing rubber equipment and filling expansion joints.

Intended Use: Repair worn or damaged rubber equipment; form protective linings in equipment subject to wear, impact, abrasion, vibration, expansion, and contraction.

Product features:
400 ml reusable cartridge
Tack-free in 30 minutes
Fast, easy, no-mess dispensing
Thorough mixing of two components with automatic mix nozzle

Limitations:

Typical Physical Properties: *Technical data should be considered representative or typical only and should not be used for specification purposes.*

Cured 7 days @ 75° F

Abrasion Resistance	330 mg loss per 1,000 revolut
Color	Grey
Coverage/lb	106 sq.in./lb. @ 1/4"
Cured Hardness	94A
Cured Shrinkage	0.0018 in./in.
Dielectric Strength	350 volts/mils
Functional Cure	2 hrs.
Maximum Elongation	450%
Maximum Operating Temperature	Dry: 180°F; Wet: 120°F
Mix Ratio	80 resin:20 curing agent /wt.
Mixed Viscosity	5,800 cps
Percent Solids by Volume	100
Pot Life	8 min. @ 75°F
Specific Volume	26.5 in.(3) /lb.
Tear Resistance	430 pli
Tensile Strength	3,300 psi

TESTS CONDUCTED

Cure Shrinkage ASTM D 2566
Dielectric Strength, volts/mil ASTM D 149
Tear Resistance ASTM D 624
Cured Hardness Shore D ASTM D 2240
Tensile Strength (Urethanes) ASTM D 412
Maximum Elongation ASTM D 412

Surface Preparation: For METAL SURFACES, thoroughly clean area to be repaired, rebuilt, or lined with Devcon® Cleaner Blend 300. Remove any oil, grease, or dirt. Roughen surface by grinding with a coarse wheel or an abrasive disc pad. To prime this surface, apply a coat of Devcon FL-10 Primer and allow to dry tack-free for 5-15 minutes. If the metal surface requires maximum tear resistance or is exposed to moisture, or if submerged in water, use Devcon® FL-10 and Devcon® FL-20 Primer.

For RUBBER SURFACES, thoroughly clean area with an abrasive pad and Devcon® Cleaner Blend 300. Surface can also be roughened with a grinding wheel so that it is coarse and free from oil and dirt that may clog the "pores" of the rubber. Wipe or roughen surface with Cleaner Blend 300 until the cloth no longer picks up the color of the rubber. The rubber should appear new or deeper in color. To prime this surface, apply a coat of Devcon® FL-20 Primer and allow to dry tack-free for 15-20 minutes. Use Devcon®FL-40 Primer on "hard-to-bond" rubber surfaces as this gives ultimate peel resistance. Multiple coats may be necessary for porous rubber surfaces.

For MAXIMUM ADHESION, sandblast the surface with an angular abrasive until a minimum depth profile of 2-3 mils is met. Blast to near-white finish specification SSPC-SP5 (Steel Structure Painting Council). Prime surface immediately after sandblasting to prevent oxidation.

Mixing Instructions: ---- To ensure proper cure speeds and hardness, mix Flexane at a temperature between 65°F-85°F. ----

FOR 1 LB. UNITS

- 1.Add hardener to resin.
- 2.Vigorously mix with screwdriver or spatula for two minutes, while continuously scraping material away from sides and bottom of container.
- 3.Transfer the mixed material to the plastic container (included in kit).
- 4.Wipe spatula clean, and stir again for two more minutes.

FOR 400ML CARTRIDGES:

1. Attach mix nozzle to cartridge
2. Follow application instructions; no mixing is required.

FOR 10LB. UNITS:

Use a propeller-type Jiffy Mixer Model ES on an electric drill.

Mix until color is uniform and consistent (approx 4-6 min.).

NOTE: Completely submerge propeller, otherwise large amounts of air will be added resulting in air bubbles on the finished product's surface.

Application Instructions:

1. Mount cartridge onto manual gun (#15043).
2. Attach #15047 mix nozzle.
3. Clip mix nozzle back to desired orifice size.
4. Squeeze cartridge, allowing first THREE INCHES of material to discharge until a unified mix is exuding from nozzle (color is uniform with no striations).
5. Finish application as quickly as possible.

IMPORTANT:

Replace mix nozzle every four minutes to ensure complete mix, with no soft spots. Because of the short pot life (8 minutes), stopping between uses can result in Flexane product curing IN the mix nozzle. Further mixing will be off ratio.

Storage:

Store at room temperature, 70 °F.

Compliances:

None

Chemical Resistance:

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F

1,1,1-Trichloroethane	Poor
Aluminum Sulfate 10%	Very good
Cutting Oil	Fair
Gasoline (Unleaded)	Poor
Hydrochloric 10%	Very good
Hydrochloric 36%	Very good
Isopropanol	Poor
Methyl Ethyl Ketone	Poor

Phosphoric 10%	Very good
Potassium Hydroxide 40%	Very good
Sodium Hydroxide 50%	Very good
Sodium Hypochlorite	Very good
Xylene	Poor

Precautions:

Please refer to the appropriate safety data sheet (SDS) prior to using this product.

For technical assistance, please call 1-855-489-7262

FOR INDUSTRIAL USE ONLY

Warranty:

ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer:

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Performance Polymers makes no representations or warranties of any kind concerning this data.

Order Information:

15050 400 ml cartridge