

103995 off white  
103975 black

# SC 1800 LS Barrier Coat



**SC 1800 LS** is a sprayable premium vinyl ester barrier coat applied directly behind the gel coat. MEKP catalyst is not included.

## PRODUCT FEATURES

- ✓ Outstanding performance when blocking skin coat print through
- ✓ Excellent gloss readings
- ✓ High tensile elongation helps prevent gel coat stress cracking
- ✓ High resistance to water permeation
- ✓ Excellent flexural strength and fatigue resistance

## PRODUCT BENEFITS

- ✓ Improves product cosmetics
- ✓ Helps increase blister resistance
- ✓ Reduces impact cracks

## TECHNICAL SPECIFICATIONS

APPEARANCE	PACKAGING	APPLICATION METHOD	APPROXIMATE COVERAGE	STYRENE
Off White/Black	Drum	Sprayable	1550 sq ft/gal/mil	22%
MIX RATIO	PREFERRED RED DYE CATALYST	GEL TIME	GEL TO PEAK RANGE	PEAK EXOTHERM (100 G MASS)
1.5%	DHD-9 MEKP 900	3-5 mins.	3-7 mins.	360-400°F
APPLICATION DENSITY RANGE	VISCOSITY	LBS/SQ FT@1MIL	LAMINATE SKIN COAT APPLICATION INTERVAL	THIX INDEX
6.2-6.8 lbs/gal	4,000-7,000 cps (HB#4@20 rpm)	0.004052	25-40 min.	3.2-4.2

All properties are measured at 77°F/25°C

# SprayCore®

ITW Performance Polymers

11701 56th Court North, Clearwater, Florida 33760

Toll Free: 1-866-470-1462 • Phone: 727-573-3545 • Fax: 727-299-9797 • Email: [spraycoreinfo@itwpp.com](mailto:spraycoreinfo@itwpp.com)

[www.itwpp.com](http://www.itwpp.com)

Rev. 3 07/2019