



TECHNICAL BULLETIN #3094 – INSULCAST MRTV 9 HIGH TEAR MOLD MAKING RTV SILICONE

Revised: 05/2018

PRODUCT DESCRIPTION

INSULCAST MRTV 9 is a high tear strength, high elongation addition cure mold making RTV silicone rubber. **MRTV 9** has low shrinkage and reproduces the most intricate detail.

PROPERTIES UNCURED

	Part A	Part B	
COLOR, VISUAL	Black	Clear	-
VISCOSITY@ 25°C, cps	1.15	1.0	ASTM D 1084
SPECIFIC GRAVITY	100000	<1,000	-
MIX RATIO (by wt.)	100:10		-
MIXED VISCOSITY, cps	50000		ASTM D 1084
SHELF LIFE @ 25°C, months	6		-
POT LIFE (100 gr.) @ 25°C, mins	1.5-2		-

PROPERTIES CURED

PHYSICAL		
HARDNESS, DUROMETER (Shore A)	24	ASTM D 2240
TENSILE STRENGTH, psi	500	ASTM D 412
TENSILE ELONGATION, %	1000	ASTM D 412
COMPRESSIVE STRENGTH, psi		-
FLEXURAL STRENGTH, psi		-
TEAR STRENGTH, Die B lb/in	117	ASTM D 624
TEAR STRENGTH, Die C lb/in	125	ASTM D 624
COEFFICIENT OF THERMAL EXPANSION, °C	4.2x10 ⁻⁴	-
THERMAL CONDUCTIVITY, BTU-in/(ft ²)(hr)(°F)	0.18	-
THERMAL CONDUCTIVITY, W/m °K	0.026	-
HEAT DISTORTION POINT, °C		-
SERVICE TEMPERATURE, °C	-55 TO +204	-

ELECTRICAL

DIELECTRIC STRENGTH, volts/mil	550	ASTM D 149
DIELECTRIC CONSTANT, 1 KHz	2.94	ASTM D 150
DISSIPATION FACTOR, 1 KHz	0.002	ASTM D 150
VOLUME RESISTIVITY, ohm-cm	1.6x10 ¹⁵	ASTM D 257

USE INSTRUCTIONS

1. Pre-mix MRTV 9 base and curing agent before use to be sure any settled filler is Re-incorporated.
2. Weigh out amount of base component required for mold. Weigh into the base one part of catalyst for each 10 parts of **MRTV 9** base.
3. Mix thoroughly, scraping both the bottom and side of the mixing container.
4. Place in a vacuum chamber and draw about 29 inches of mercury. The mixture will rise to about 3-4 times its original volume, then collapse. Hold the vacuum for another minute or two and release.
5. Proceed to pour mold.

CURE SCHEDULE

16-24 hours @ Room Temperature (25°C)
 3 - 4 hours @50°C
 1 - 2 hours @65°C

STORAGE REQUIREMENTS

This product may settle upon shipment or storage. The product should be re-mixed well prior to use. Store material in a cool dry place.

SPECIAL NOTES

Certain materials may inhibit the cure of **MRTV 9** when placed in contact with the mixed, uncured rubber. Materials such as amines and amine cured epoxies, sulfur containing materials and condensation (tin cured) silicones, are some which may cause inhibition. Even surfaces which have been in contact with such materials may cause it. If in doubt, a patch test should be done.

IMPORTANT:

The following supersedes any provision in your company's forms, letters and papers. ITW PERFORMANCE POLYMERS makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW PERFORMANCE POLYMERS BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW PERFORMANCE POLYMERS for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW PERFORMANCE POLYMERS sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clean water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION. FOR CHEMICAL EMERGENCY, CALL CHEMTREC (DAY OR NIGHT) 800 424-9300.



ITW Philadelphia Factor
 Registered on ISO 9001:2008
 File No. 13750



ITW Performance Polymers Europe
 ISO 9001:2008
 Q 06-028