



## TECHNICAL BULLETIN #3080 – RTVS 27 LV LOW VISCOSITY, RTV POTTING/CASTING COMPOUND

Revised: 05/2018

### PRODUCT DESCRIPTION

**RTVS 27 LV** is a low viscosity, general purpose, reversion resistant RTV Silicone Compound and finds use in commercial potting/casting applications. **RTVS 27 LV** one-to-one ratio by weight or volume makes it ideal for dispensing equipment or unskilled labor. With the ability to cure rapidly at elevated temperatures, **RTVS 27 LV** can be processed quickly in production situations, and meets the requirements of UL 94V-0.

### PROPERTIES UNCURED

	Part A	Part B	
COLOR, VISUAL	Black	Buff	-
VISCOSITY, cps	1,200	1,200	ASTM D 1084
SPECIFIC GRAVITY	1.47	1.47	-
MIX RATIO (by weight or volume)	1:1		-
MIXED VISCOSITY, cps	1,200		ASTM D 1084
POT LIFE @ 25°C, hours	2		-
SHELF LIFE @ 25°C, months	12		-

**PROPERTIES CURE**

PHYSICAL		
HARDNESS, DUROMETER, Shore A	60	ASTM D 2240
TENSILE STRENGTH, psi	500	ASTM D 412
TENSILE ELONGATION, %	100	ASTM D 412
TEAR STRENGTH, Die B lb/in	15	ASTM D 624
COEFFICIENT OF THERMAL EXPANSION, °C	22x10 <sup>-5</sup>	-
LINEAR SHRINKAGE, %	0.2	-
THERMAL CONDUCTIVITY, BTU-ft/(ft <sup>2</sup> )(hr)(°F)	0.18	-
THERMAL CONDUCTIVITY, BTU-in/(ft <sup>2</sup> )(hr)(°F)	2.16	-
USEFUL TEMPERATURE RANGE, °C	-55 to +204	-

**ELECTRICAL**

DIELECTRIC STRENGTH, volts/mil	500	ASTM D 149
DIELECTRIC CONSTANT, 1 KHz	3.4	ASTM D 150
DISSIPATION FACTOR, 1 KHz	0.004	ASTM D 150
VOLUME RESISTIVITY, ohm-cm	3.0x10 <sup>14</sup>	ASTM D 257

**MIXING INSTRUCTIONS**

1. Pre-mix **RTVS 27 LV** Parts A and B in original containers before withdrawing any material. Some light but soft settling may occur, which readily re-disperses.
2. Measure equal portions of Parts A and B (by weight or volume).
3. Mix thoroughly.
4. Where absolutely void-free castings are required, evacuate the mixed **RTVS 27 LV** at 29 in. Hg for 3-4 minutes.
5. Pour into unit or mold.

**CURE SCHEDULE**

Overnight at room temperature (24 hours at 25°C.) **OR**, one (1) hour at 60°C., **OR** 15 minutes at 95°C.

**SPECIAL NOTES**

Certain materials may inhibit the cure of **RTVS 27 LV** when placed in contact with the mixed, uncured rubber. Materials such as amines and amine cured epoxies, sulfur containing materials and condensation (tin cured) silicones, are some which may cause inhibition. Even surfaces which have been in contact with such materials may cause it. If in doubt, a patch test should be done.

**IMPORTANT:**

The following supersedes any provision in your company's forms, letters and papers. ITW PERFORMANCE POLYMERS makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW PERFORMANCE POLYMERS BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW PERFORMANCE POLYMERS for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW PERFORMANCE POLYMERS sole opinion, to justify such refund.

**HEALTH CAUTION:**

Avoid breathing possible fumes, mists and vapors which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clean water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

**PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION. FOR CHEMICAL EMERGENCY, CALL CHEMTREC (DAY OR NIGHT) 800 424-9300.**