



TECHNICAL BULLETIN #3084 – RTVS 46 LOW DENSITY RTV SILICONE COMPOUND

Revised: 05/2018

PRODUCT DESCRIPTION

RTVS 46 is a pourable RTV Silicone sealing/potting compound which cures to a flexible syntactic foam. **RTVS 46** finds use in applications involving air-borne or “man-pack” equipment. **RTVS 46** is suggested for use in circuitry requiring low capacitance, low dielectric constant and low dissipation.

PROPERTIES UNCURED

COLOR, VISUAL	White	-
VISCOSITY, cps mixed	40,000	ASTM D 1084
SPECIFIC GRAVITY	0.71	-
MIX RATIO (by weight)	100:5	-
POT LIFE @ 25°C, minutes	2-3	-
SHELF LIFE @ 25°C, months	6	-

PROPERTIES CURED

PHYSICAL		
HARDNESS, DUROMETER, Shore A	30	ASTM D 2240
TENSILE STRENGTH, psi	700 min.	ASTM D 412
TENSILE ELONGATION, %	120 min.	ASTM D 412
WATER ABSORPTION, (24 hrs. @ 25°C %)	0.1	-
COEFFICIENT OF THERMAL EXPANSION, °C	20x10 ⁻⁵	-
THERMAL CONDUCTIVITY, BTU-ft/(ft ²)(hr)(°F)	0.15	-
THERMAL CONDUCTIVITY, BTU-in/(ft ²)(hr)(°F)	1.8	-
SERVICE TEMPERATURE, °C	-50 to 204	-

ELECTRICAL

DIELECTRIC STRENGTH, volts/mil	250	ASTM D 149
DIELECTRIC CONSTANT, 1 KHz	2.6	ASTM D 150
DISSIPATION FACTOR, 1 KHz	0.004	ASTM D 150
VOLUME RESISTIVITY, ohm-cm	1.0x10 ¹⁴	ASTM D 257

MIXING INSTRUCTIONS

1. Pre-mix **RTVS 46** in its original container to reincorporate any filler that may have separated.
2. Weigh out required amount of RTVS 46.
3. Measure the amount of Catalyst Part B required.
4. Mix thoroughly, scraping the sides and bottom of container.
5. Pour into cavity or mold.

CURE SCHEDULE

Overnight at room temperature (24 hours at 25°C).

IMPORTANT:

The following supersedes any provision in your company's forms, letters and papers. ITW PERFORMANCE POLYMERS makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW PERFORMANCE POLYMERS BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW PERFORMANCE POLYMERS for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW PERFORMANCE POLYMERS sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clean water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION. FOR CHEMICAL EMERGENCY, CALL CHEMTREC (DAY OR NIGHT) 800 424-9300.