



DFense Blok™ Fast Cure (FC)

Description: Alumina ceramic bead-filled epoxy system with outstanding wear and abrasion resistance for severe service conditions. Fast cure allows for repaired processing equipment to be returned to service in as little as 2 hours.

Intended Use: Industrial Use: Repair scrubbers, ash handling systems, pipe elbows, screens, chutes, chippers, bins, hoppers, bunkers, separators and digester tables. Protect exhausters, launderers, housing fans, crushers, breakers, and conveyor screws.

Features: **Fast cure for minimal downtime, Superior wear and abrasion resistance, Able to withstand impact**
Resistant to a wide range of chemicals, Non-sagging

Limitations: Suitability of product is determined by the end user for their application and process.

Typical Physical Properties: Technical data should be considered representative or typical only and should not be used for specification purposes.

Cured 7 Days @ 75°F (24°C)

Adhesive Tensile Shear	2,764 psi (19 MPa)
Coefficient of Thermal Expansion (x10-6)	33 in/in.°F (59.4 cm/cm.°C)
Color	Grey
Compressive Strength	7,178 psi (49.5 MPa)
Cured Hardness	80 D
Cured Shrinkage	0.0008 in/in (cm/cm)
Dielectric Constant	45
Flexural Strength	7,488 psi (51.6 MPa)
Recoat Time	1 to 1.5 hours
Specific Gravity	17.11 lb/Gal (2.05 g/cm3)
Specific Volume	13.5 in3/lb (0.488 cm3/g)
Temperature Resistance	Dry 300°F (149°C) Wet 140°F (60°C)

Standard Tests

Adhesive Tensile Shear	ASTM D 1002
Compressive Strength	ASTM D 695
Cured Hardness Shore D	ASTM D 2240
Cure Shrinkage	ASTM D 2566
Dielectric Constant	ASTM D 150
Flexural Strength	ASTM D 790
Coef. of Thermal Expansion	ASTM D 696

Uncured Properties @ 72°F (23°C)

% Solids by Volume	100
Coverage (1/4" / 6.35mm)	53 in2/lb (754cm2/Kg)
Cure Time	10 hrs
Functional Cure	2-3 hrs
Mix Ratio by Volume	2:1
Mix Ratio by Weight	2:1
Mixed Viscosity	Non-Sag Putty
Pot Life @ 75 °F (24 °C)	15 mins.

Surface Preparation:

1. Thoroughly clean the surface with Devcon® Cleaner Blend 300 to remove all oil, grease and dirt.
2. Grit blast surface area with 8-40 mesh grit, or grind with a coarse wheel or abrasive disc pad, to create increased surface area for better adhesion (Caution: An abrasive disc pad can only be used provided white metal is revealed). Desired profile is 3-5mil, including defined edges (do not "feather-edge" epoxy).

Note: For metals exposed to sea water or other salt solution, grit-blast and high-pressure-water-blast the area, then leave overnight to allow any salts in the metal to "sweat" to the surface. Repeat blasting to "sweat out" all soluble salts. Perform chloride contamination test to determine soluble salt content (should be no more than 40ppm).

3. Clean surface again with Devcon® Cleaner Blend 300 to remove all traces of oil, grease, dust or other foreign substances from the grit blasting.
4. Repair surface as soon as possible to eliminate any changes or surface contaminants.

WORKING CONDITIONS: Ideal application temperature is 55°F to 90°F (13°C- 32°C). In cold working conditions, directly heat repair area to 100-110°F (38-43°C) prior to applying epoxy and maintain at this temperature during product cure to dry off any moisture, contamination or solvents, as well as to achieve maximum performance properties.

Mixing Instructions: ---- It is strongly recommended that full units be mixed, as ratios are pre-measured. ----

1. Add hardener to resin
2. Mix thoroughly with screwdriver or similar tool (continuously scrape material away from sides and bottom of container) until a uniform, streak-free consistency is obtained.

INTERMEDIATE SIZES (1,2,3 lb. units): Place resin and hardener on a flat, disposable surface such as cardboard plywood or plastic sheet. Use a trowel or wide-blade tool to mix the material as in Step 2 above

LARGE SIZES: (25 lb., 30 lb., 50 lb. buckets): Use a T-shaped mixing paddle or a propeller-type Jiffy Mixer Model ES on an electric drill. Thoroughly fold putty by vigorously moving paddle/propeller up and down until a homogenous mix of resin and hardener is attained.

Application Instructions:

Spread mixed material on repair area at a minimum thickness of 1/4" (6.4mm). Work firmly into substrate to ensure maximum surface contact. Dfense Blok™ Fast Cure (FC) fully cures in 10 hoppp. Application Tip: For easier "workability," a light coating of Devcon® Cleaner Blend 300 or 99% Isopropyl Alcohol (IPA) on the surface of the tool used to transfer/spread Dfense Blok™ Fast Cure (FC) is recommended.

FOR BRIDGING LARGE GAPS OR HOLES

Place fiberglass sheet, expanded metal or mechanical fasteners between repair area and Dfense Blok™ Fast Cure (FC) prior to application.

Let bonded assemblies stand for recommended functional cure time prior to handling.

FOR VERTICAL SURFACE APPLICATIONS

Dfense Blok™ Fast Cure (FC) can be troweled up to 3/4" (19mm) without sagging. If greater vertical thickness is desired, apply first layer at 3/4" (19mm), wait until product is firm and heat of reaction dissipates, apply a second layer of 3/4" (19mm). Repeat as needed.

FOR OVERHEAD APPLICATIONS

Dfense Blok™ Fast Cure (FC) can be applied up to 1/2" (12.5mm) to overhead surfaces. If greater thickness is desired apply first layer at 1/2" (12.5mm), wait until product has firmed and heat of reaction dissipates, apply a second layer at 1/2" (12.5mm). Repeat as necessary.

FOR ± 70°F (21°C) APPLICATIONS

Applying epoxy at temperatures below 70°F (21°C) lengthens functional cure and pot lifetimes. Conversely, applying above 70°F (21°C) shortens functional cure and pot life.

Storage:

Store at room temperature, 70°F (21°C).

Compliances:

None

Chemical**Resistance:**

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F (24°C)

1,1,1-Trichlorethane	Very good
Ammonia	Excellent
Gasoline (Unleaded)	Fair
Hydrochloric 10%	Very good
Methanol	Poor
Methyl Ethyl Ketone	Poor

Trisodium Phosphate	Very good
Sodium Hydroxide, 50%	Excellent
Sulfuric 10%	Very good

Precautions:

FOR INDUSTRIAL USE ONLY: Please refer to the appropriate Safety Data Sheet prior to using this product.

Warranty:

ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Order Information:

Item No.	Package Size
11350	9 lb. (4.1 Kg)

Contacts:

www.itwpp.com

ITW Performance Polymers (EMEA)

Bay 150, Shannon Industrial Estate
Shannon, County Clare, Ireland V14 DF82
TEL: +353 61 771 500
FAX: +353 61 471 285
Email: customerservice.shannon@itwpp.com

ITW Performance Polymers (US)

30 Endicott Street
Danvers, MA 01923 USA
TEL: 855 489 7262
FAX: 978 774 0516
Email: info@itwpp.com

Disclaimer:

Product Use: The information herein is based upon good faith testing that ITW PP believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW PP control and uniquely within user's knowledge and control can affect the use and performance of an ITW PP product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsible for evaluating any ITW PP product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.

Exclusion of Warranties: As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW PP makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW PP shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.