



Deep Pour Grout™

Description:	Filled epoxy grout for pouring machinery mounting pads to 6" deep and for rebuilding worn concrete.
Intended Use:	Industrial Use: For leveling compressors; generators; blowers; lathes; ball mills; engines; pulverizers; large pump bases and milling machines
Features:	Easy to mix Self-leveling Bonds to metal and concrete Low shrinkage Resists industrial chemicals
Limitations:	Suitability of product is determined by the end user for their application and process.

Typical Physical Properties: Technical data should be considered representative or typical only and should not be used for specification purposes.

Cured 7 Days @ 75°F (24°C)	Typical Values	Standard Tests
Color	Grey	
Compressive Strength	17,250 psi (119 MPa) Cure	Compressive Strength ASTM D 695
Cured Hardness	83D	Cured Hardness Shore D ASTM D 2240
Functional Cure	16 hours	
Minimum Recoat Time @ 75F (24 C)	2 - 3 hrs.	
Mixed Density	18.1 lbs/gal (2.17 g/cm3)	
Temperature Resistance	180°F (82°C)	
Uncured		
% Solids by Volume	100	
Application Coverage	12.8 in3/lb (464.6 cm3/kg)	
Application Temperature	50° - 90° F (10- 32°C)	
Mix Ratio (Resin/Hard. Mix to Aggr.)	1:3.9 by weight ; 1:1.8 by volume	
Mix Ratio (Resin/Hardener)	4.5:1 by weight ; 4.2:1 by volume	
Mixed Viscosity	13,000 cP	
Pot Life @ 75°F (Full kit)	40 minutes	

Surface Preparation: For METAL SURFACES, use a wire brush or sandpaper to remove rust and scale from the surface to be protected. Surfaces may be shot blasted or abraded using a wire wheel for best results. All dirt, grease, and old paint should be removed. A clean, dry surface is essential for the best results.

Begin with a sound, clean, dry and roughened, oil-free application surface, as it is essential to the success and performance of this product.

Spot test surface by mixing a small quantity of the resin and hardener without the silica filler. Apply the compound to a small, clean test area. Old paint may wrinkle or lift. If it DOES NOT, wait five (5) days and test the bond strength by scraping surface with a sharp instrument. A pressure-sensitive tape test can also be used as follows: cut an "X" into surface and place tape firmly over the cut. Remove the tape with a hard, fast pull. If the coating fails either test, proceed with instructions for previously coated concrete (see below).

For NEW POURED CONCRETE, allow to fully cure (28 days @ 70°F (21°C) prior to application. Remove any curing membrane by sanding or etching with a strong detergent.

For OLD CONCRETE, thoroughly clean surface with a grease-cutting detergent to remove grease and oils, and remove any loose or unsound concrete by chipping, scarifying, shotblasting, sanding, or grinding. Proceed as for new poured concrete.

For PREVIOUSLY COATED CONCRETE, applications should be considered short term because the coating system is only as strong as its weakest component. Remove any peeling or degraded paint by sanding or using a paint stripper. For intact paint, thoroughly clean the surface with a strong detergent, then lightly sand to remove any gloss. Treat any areas worn down to the original concrete as bare concrete.

Mixing Instructions: ---- Adequate ventilation is necessary when mixing this product.----

- Attach a propeller-type Jiffy Mixer Model ES to an electric drill.
- Shake Resin and hardener well before use.
- Add resin to pail and mix thoroughly until color is uniform.
- Add hardener into resin pail.
- Mix for about two (2) minutes, while continuously scraping material away from sides and bottom of container.
- Slowly and evenly, pour aggregate into liquid mixture and mix until a uniform texture is obtained.

**Application
Instructions:**

1. Pour grout as soon as possible after mixing.
2. In well ventilated areas, pour from one side letting air escape out of the cavity.
3. In restricted or tight areas, use steel rods to help grout flow (only if necessary).

CURE SCHEDULE:

Temp (F) (C)	Working Time	Functional Cure
55°F 12.7	1 hour	36 hours
70°F 21.1	40 min.	24 hours
80°F 26.6	30 min.	20 hours
90°F 32.2	20 min.	18 hours

Storage:

Shelf life 3 yrs from manufacture. See package label. Store at room temperature, 70 °F (21°C)

Compliances:

Approved in the U.S. for use in meat and poultry processing plants.
Accepted by Canadian Department of Agriculture Food Safety Service.

**Chemical
Resistance:**

Chemical resistance is calculated with a 7-day, room temp. cure (30 days immersion) @ 75°F (24°C)

Ammonia	Very good
Chlorinated Solvent	Very good
Hydrochloric 10%	Poor
Kerosene	Excellent
Methanol	Poor
Sodium Hydroxide 10%	Excellent
Sulfuric 10%	Poor
Toluene	Poor

Precautions:

FOR INDUSTRIAL USE ONLY: Please refer to the appropriate Safety Data Sheet prior to using this product.

Warranty:

ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

**Order
Information:**

<u>Item No.</u>	<u>Package Size</u>
13800	50 lb. (22.6 kg)

Contacts:

www.itwpp.com

ITW Performance Polymers (EMEA)
Bay 150, Shannon Industrial Estate
Shannon, County Clare, Ireland V14 DF82
TEL: +353 61 771 500
FAX: +353 61 471 285
Email: customerservice.shannon@itwpp.com

ITW Performance Polymers (US)
30 Endicott Street
Danvers, MA 01923 USA
TEL: 855 489 7262
FAX: 978 774 0516
Email: info@itwpp.com

Disclaimer:

Product Use: The information herein is based upon good faith testing that ITW PP believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW PP control and uniquely within user's knowledge and control can affect the use and performance of an ITW PP product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsible for evaluating any ITW PP product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.

Exclusion of Warranties: As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW PP makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW PP shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.