



Epoxy Coat™ 7000 AR

Description:	An acid-resistant, room-temperature cured, 100% solids, epoxy coating
Intended Use:	Industrial Use: Ideal coating for chemical storage tanks, dike walls, and containment areas where chemical resistance to acids are needed
Features:	High build (8-10 mils) (0.20-0.25 mm) Superior resistance to concentrated acids (including 98% sulfuric) Applies with brush or roller Excellent adhesion to concrete surfaces Novolac resin
Limitations:	Suitability of product is determined by the end user for their application and process. Not recommended for outdoor use

Typical Physical Properties: Technical data should be considered representative or typical only and should not be used for specification purposes.

Cured 7 Days @ 75°F (24°C)

Hardness
Solids by Volume
Temperature Resistance

Typical Values

85 Shore D
100%
Wet: 130°F (54°C); Dry: 200°F (93°C)

Standard Tests

Shore Hardness ASTM D2240

Uncured Properties @ 72°F (23°C)

Application Temperature 60-90°F (16-32°C)
Color Gray
Coverage (16 mil / 0.4mm) 100 ft²/Gal (2.5m²/L)
Cure Time 24 hrs
Cure Time - Full Chemical 10 days
Cure Time - Full Service 48 hrs
Functional Cure 24 hrs.
Minimum Recoat Time @ 75F 4-6 hrs.
Mix Ratio 1.7:1 by weight./1.5:1 by volume
Mixed Viscosity 3,600 cP
Pot Life @ 75F 36 min.

Surface Preparation: For METAL SURFACES, use a wire brush or sandpaper to remove rust and scale from the surface to be protected. Surfaces may be shot blasted or abraded using a wire wheel for best results. All dirt, grease, and old paint should be removed. A clean dry surface is essential for the best results.

Begin with a sound, clean, dry and roughened, oil-free application surface, as it is essential to the success and performance of this product.

Spot test surface by mixing a small quantity of the resin and hardener without the silica filler. Apply the compound to a small, clean test area. Old paint may wrinkle or lift. If it DOES NOT, wait five (5) days and test the bond strength by scraping surface with a sharp instrument. A pressure-sensitive tape test can also be used as follows: cut an "X" into surface and place tape firmly over the cut. Remove the tape with a hard, fast pull. If the coating fails either test, proceed with instructions for previously coated concrete (see below).

For NEW POURED CONCRETE, allow to fully cure (28 days @ 70°F (21°C)) prior to application. Remove any curing membrane by sanding or etching with a strong detergent.

For OLD CONCRETE, thoroughly clean surface with a grease-cutting detergent to remove grease and oils, and remove any loose or unsound concrete by chipping, scarifying, shotblasting, sanding, or grinding. Proceed as for new poured concrete.

For PREVIOUSLY COATED CONCRETE, applications should be considered short term because the coating system is only as strong as its weakest component. Remove any peeling or degraded paint by sanding or using a paint stripper. For intact paint, thoroughly clean the surface with a strong detergent, then lightly sand to remove any gloss. Treat any areas worn down to the original concrete as bare concrete.

Mixing Instructions:

1. Pour hardener into resin.
2. Mix for about three (3) minutes using a propeller-type Jiffy Mixer Model ES (or equivalent) until a uniform color is achieved.

Application Instructions: For best results, Epoxy Concrete Sealer should be stored and applied at room temperature.

PRIOR TO APPLICATION:

1. Fill large holes with a patching compound (Devcon Floor Patch or Devcon Ultra Quartz is recommended).

APPLICATION:

Apply Epoxy Coat 7000 AR onto floor with a notched squeegee, then "back roll" for a smooth finish (a 3/8" (9.5 mm) or 0.5 in. (12.5 mm) nap roller is recommended for best results). Coverage will vary based on surface conditions.

After applying the first coat, the need for a second coat can be assessed based on floor condition and end user's objectives. When applying a second layer, the minimum recoat time recommendation is 8-10 hours.

Epoxy Coat 7000 AR produces a smooth finish, which can be slippery, especially when wet. To prevent slipping, add a non-skid aggregate, such as ground walnut shells or dry sand, to the coating.

Storage: Store at room temperature, 70°F (21°C).

Compliances: Approved in the U.S. for use in meat and poultry processing plants.
Accepted by Canadian Department of Agriculture Food Safety Service.

Chemical Resistance: Chemical resistance is calculated with a 7-day, room temp. cure (30 days immersion) @ 75°F (24°C)

Acetic (Dilute) 10%	Poor	Nitric 50%	Fair
Cutting Oil	Excellent	Phosphoric 50%	Excellent
Gasoline (Unleaded)	Excellent	Potassium Hydroxide 40%	Very good
Methanol	Excellent	Sodium Hydroxide 50%	Excellent
Methyl Ethyl Ketone	Poor	Sodium Hypochlorite	Excellent
Hydrochloric 36%	Poor	Sulfuric 10%	Excellent
Methylene Chloride	Poor	Sulfuric 50%	Excellent
Nitric 10%	Excellent	Toluene	Excellent

Precautions: **FOR INDUSTRIAL USE ONLY:** Please refer to the appropriate Safety Data Sheet prior to using this product.

Warranty: ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Order Information:

<u>Item No.</u>	<u>Package Size</u>
12750	2 gal. (7.56 Liter)

Contacts:

www.itwpp.com ITW Performance Polymers (EMEA) Bay 150, Shannon Industrial Estate Shannon, County Clare, Ireland V14 DF82 TEL: +353 61 771 500 FAX: +353 61 471 285 Email: customerservice.shannon@itwpp.com	ITW Performance Polymers (US) 30 Endicott Street Danvers, MA 01923 USA TEL: 855 489 7262 FAX: 978 774 0516 Email: info@itwpp.com
--	---

Disclaimer: **Product Use:** The information herein is based upon good faith testing that ITW PP believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW PP control and uniquely within user's knowledge and control can affect the use and performance of an ITW PP product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsible for evaluating any ITW PP product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.

Exclusion of Warranties: As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW PP makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW PP shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.