



Korrobond 65 Epoxy Crusher Backing Compound

Description: Korrobond 65 (aka, High Performance) is a two-component epoxy backing compound specifically designed for various mining and quarrying applications. It serves as a backing and reinforcing layer between machine parts and as a damper when subjected to impact and shock loads.

Intended Use: Industrial Use: Mining crusher equipment

Features:
Very high compressive strength
100% Solids, minimal shrinkage
Easy to mix and pour
Long established OEM
Aftermarket proven product
High impact strength and resilience

Limitations: Suitability of product is determined by the end user for their application and process.

Typical Physical Properties: Technical data should be considered representative or typical only and should not be used for specification purposes.

Cured 7 Days @ 75°F (24°C)	Typical Values	Standard Tests
Adhesive Lap Shear Strength	> 354 Kg/m ²	Adhesive Tensile Shear ASTM D 1002
Adhesive Tensile Strength	>27 MPa / 4,000 psi	Tensile Strength (Epoxy) ASTM D 638
Compressive Strength	135 +/-7 MPa / 19,500 +/-1000 PSI	Cure Shrinkage ASTM D 2566
Cure Shrinkage	0.01%	Compressive Strength ASTM D 695
Solids by Volume	100%	

Uncured Properties @ 72°F (23°C)	
Color	Light Grey
Density	14.86 lb/Gal (1.78 g/cm ³)
Functional Cure	8-10 hr
Mix Ratio by Volume	7 Resin ; 1 Hardener
Mix Ratio by Weight	13.3 : 1.0
Mixed Viscosity	> 20,000 cP
Pot Life @ 75°F (24°C)	15-20 minutes

Application: It is recommended that Korrobond 65 is brought to an optimum working temperature of circa 25°C/74 °F by placing it in a warm room 24 hours prior to use. At lower temperatures the material will be more viscous and hence difficult to pour and at temperatures above 30°C/86 °F the pot life of the product will be reduced. At temperatures below 5°C/41°F and above 40°C/104°F casting should not be carried out.

Prior to use the respective crusher manufacturer's instructions should be consulted.

Mixing: Korrobond 65 is supplied as two components, in the 10Kg kit these are pre-weighed to remove any potential for issues regarding ratio. As such these kits should only be completely mixed and not be broken down.

A suitable mixing device is required, e.g., a suitable drill with mixing paddle. Stir Part A until homogenous then add Part B and continue mixing until to two components are homogenous.

Clean Up: Any tools used in the mixing and application of Korrobond 65 should be cleaned in methylated spirit immediately after use, as Korrobond 65 is difficult to remove once cured.

Storage & Shelf Life: A shelf life of 24 months from date of manufacture can be expected for this product when stored at room temperature (~22°C/72°F) in their original containers.

Precautions: **FOR INDUSTRIAL USE ONLY:** Please refer to the appropriate Safety Data Sheet prior to using this product. For complete safety and handling information, please refer to the appropriate Safety Data Sheets prior to using this product.

Compliances: None

Order Information: 81065 Korrobond 65 10 kg / 22 lb Kit
81070 Korrobond 65 20 kg / 44 lb Kit
81065D Korrobond 65 285 kg / 628 lb Drum Kit

Warranty: ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Contacts: www.itwpp.com

ITW Performance Polymers (EMEA) Bay 150, Shannon Industrial Estate Shannon, County Clare, Ireland V14 DF82 TEL: +353 61 771 500 FAX: +353 61 471 285 Email: customerservice.shannon@itwpp.com	ITW Performance Polymers (US) 30 Endicott Street Danvers, MA 01923 USA TEL: 855 489 7262 FAX: 978 774 0516 Email: info@itwpp.com
--	---

Disclaimer: **Product Use:** The information herein is based upon good faith testing that ITW PP believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW PP control and uniquely within user's knowledge and control can affect the use and performance of an ITW PP product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsibility for evaluating any ITW PP product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.

Exclusion of Warranties: As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW PP makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW PP shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.