

SC6000 Coring Print Blocker

Description: **SC 6000 Coring/Print Blocker** is a unique micro balloon syntactic resin that can be used in a variety of ways to enhance the cosmetic appearance, rigidity, and the speed of fiberglass reinforced plastic products. MEKP Catalyst is not included.

Item Number 103201 6000 drum unlined

FEATURES & BENEFITS

- Attractive alternative to plywood, PVC foam cores, end grained balsa and polyester mats
- Lightweight material with low exotherm offer minimal shrinkage.
- Greatly reduces the transfer of the fiberglass patten of laminates
- Speeds up production with its fast gel and cure times
- Helps reduce finishing costs
- Can be used with internal/external spray systems

TYPICAL MATERIAL PROPERTIES

Appearance	Packaging	Application Method	Approximate Coverage
White	Drum	Sprayable	1550 sq ft/gal/mil
Mix Ratio	Preferred red dyed Catalyst	Gel Time, min.	Gel to Peak Range, min.
1.5 % MEKP	MEKP-9 DHD-9 MEKP-900	5 - 10	15 - 20
Styrene	Peak Exo. Temp. (100 gm) °F / °C	Density Range, lb/gal	Viscosity Range, cP
31%	200-250F / 93-121C	5.80 – 6.40	13,000 – 15,000 (RVF#5@20 rpm)

All properties are measured at 77°F / 25°C

SprayCore[®]

ITW Performance Polymers
30 Endicott Street Danvers, MA 01923
USA TEL: 855-489-7262

SC6000 Coring/ Print Blocker

EFFECT OF TEMPERATURE:

Application at temperatures between 65°F (18°C) and 95°F (35°C) will ensure proper cure, ideally above 75°F. Temperatures below 65°F (18°C) or above 95°F (35°C) will slow down or increase cure rate significantly. To ensure consistent dispensing between equipment, resin and catalyst, temperatures should be held reasonably constant throughout the year. Resin in cured state behaves differently at elevated and low temperatures. See ITW Performance Polymers for specific values.

STORAGE AND SHELF LIFE:

Expected Shelf life of 3 months, where shelf life is based on continuous storage between 54°F (12°C) and 95°F (35°C). Prolonged exposure above 95°F (35°C) quickly diminishes the reactivity of the product and should be avoided.

PRODUCT USE:

Many factors beyond ITWPP's control and uniquely within user's knowledge and control can affect the use and performance of an ITWPP product in an application. Given the variety of factors that can affect the use and performance of our products, the user is solely responsible for evaluating the ITWPP product and determining whether it is fit for a particular purpose and suitable for the user's method of application. ITWPP recommends the User review all Safety Data Sheets, Technical Data Sheets and ITWPP's warranty and limited liabilities prior to use. These can be found at www.itwpp.com

Notes

1. ITW PP strongly recommends that all substrates be tested with the selected laminate in the anticipated service conditions to determine suitability.
2. Industrial Use Only

DISCLAIMERS:

TECHNICAL INFORMATION: The technical information in, recommendations and other statements contained in this document are based upon good faith tests or experience that ITWPP believes are reliable, but the accuracy or completeness of such information is not guaranteed. The information provided is not intended to substitute for the customer's own testing.

EXCLUSION OF WARRANTIES: AS TO THE HEREIN DESCRIBED MATERIALS AND TEST RESULTS, THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. ITW PP MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SINCE THE USE OF THE HEREIN DESCRIBED INVOLVES MANY VARIABLES IN METHODS OF APPLICATION, DESIGN, HANDLING, AND/OR USE, THE USER, IN ACCEPTING AND USING THESE MATERIALS, ASSUMES ALL RESPONSIBILITY FOR THE END RESULT. ITW PP SHALL NOT OTHERWISE BE LIABLE FOR LOSS OF DAMAGES, WHETHER DIRECT, INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL, REGARDLESS OF THE LEGAL THEORY ASSERTED, INCLUDING NEGLIGENCE, WARRANTY, OR STRICT LIABILITY.

SprayCore[®]

ITW Performance Polymers
30 Endicott Street Danvers, MA 01923
USA TEL: 855-489-7262
FAX: 978-774-0516
e-mail: info@itwpp.com