



# Ultra Quartz™

**Description:** A heavy-duty, premium Concrete & Masonry floor patching system. Primer/Sealer systems are sold separately.

**Intended Use:** Industrial Use: Intended for repairing concrete or masonry structures, tanks or floors in chemical environments where heavy concentrations of acids, alkalis, and hydrocarbons destroying the floor. Ideal for rebuilding floors around acid dip tanks, pump pads, and secondary containment areas

**Features:**

- Trowelable to a non-porous finish
- 9000 psi (62 MPa) compressive strength
- Superior adhesion to cured concrete
- Non-sag formulation
- Outstanding resistance to acids, alkalis, water, oils, solvents, chemicals

**Limitations:** Suitability of product is determined by the end user for their application and process.

**Typical Physical Properties:** Technical data should be considered representative or typical only and should not be used for specification purposes.

Cured 7 Days @ 75°F (24°C)	Typical Values	Standard Tests
Compressive Strength	9,000 psi (62 MPa)	Compressive Strength ASTM D 695
Temperature Resistance	Wet: 120°F (49°C) ; Dry: 250°F (121°C)	Shore D ASTM D 2240
Uncured		
Application Temperature	60° - 90°F (16° - 32°C)	
Color	Light Sand	
Coverage (1/4" / 6.35mm)	0.371 ft <sup>2</sup> /lb (760.7 cm <sup>2</sup> /Kg)	
Functional Cure	16 hrs @ 75°F (24°C)	
Hardness	95 Shore D	
Mix Ratio	2 resin :1 hardener by weight	
Mix Ratio Aggregate:Liquid	10:1 by weight	
Mixed Viscosity	Putty - Paste	
Pot Life @ 75F	60 min.	
Recoat time	6-8 hrs	
Solids by Volume	100	
Specific Volume	0.498 cm <sup>3</sup> /g	

**Surface Preparation:** **Concrete & Masonry:** Begin with a sound, clean, dry and roughened, oil-free application surface, as it is essential to the success and performance of this product. For proper surface preparation, refer to Concrete or Masonry Surface Preparation as detailed by: **SSP/NACE SSPC-SP13/NACE 6**, or **ICRI No. 310.2R, CSP 3-5**. for proper surface preparation guidelines. As seen in the Application section below, **a primer sealer is required**.

Atmospheric: SSPC-SP13/NACE 6, or ICRI No. 310.2R, CSP 3-5  
 Immersion: SSPC-SP13/NACE 6-4.3.1 or 4.3.2 or ICRI No. 310.2R, CSP 3-5

**Precautions:** NEW Poured concrete, allow to fully cure (28 days @ 70°F (21°C)) prior to application. Remove any curing membrane by sanding or etching with a strong detergent. Remove any laitance if present.

OLD CONCRETE, thoroughly clean surface with a grease-cutting detergent to remove grease and oils, and remove any loose or unsound concrete by chipping, scarifying, shotblasting, sanding, or grinding. Proceed as for new poured concrete.

PREVIOUSLY COATED CONCRETE, applications should be considered short term because the coating system is only as strong as its weakest component. Remove any peeling or degraded paint by sanding or using a paint stripper. For intact paint, thoroughly clean the surface with a strong detergent, then lightly sand to remove any gloss. Treat any areas worn down to the original concrete as bare concrete.

**Metal:** If metal is also being coated, **Primer is required**. It is recommended to use a wire brush or sandpaper to remove rust and scale from the surface to be protected. Surfaces may be shot blasted or abraded using a wire wheel for best results. All dirt, grease and old paint should be removed. A clean dry surface is essential for the best results. A metal primer is required and is sold separately. See **SSPC-SP1** or **SSPC-SP10/Nace2** for metal cleaning. Optimal profile 2 mils / 50 microns

Atmospheric: SSPC-SP6/NACE 3, ISO 8501-1 Sa2 ,2 mil (50 micron) profile Immersion: SSPC-SP10/NACE 2, ISO 8501-1 SA2.5, 2-3 mil (50-75 micron) profile
----------------------------------------------------------------------------------------------------------------------------------------------------------

**Mixing** ---- Adequate ventilation is necessary when mixing this product.----

**Instructions:**

- Attach a propeller-type Jiffy Mixer Model ES to an electric drill.
- Shake Resin and hardener well before use.
- Add resin to pail and mix thoroughly until color is uniform.
- Add hardener into resin pail.
- Mix for about two (2) minutes, while continuously scraping material away from sides and bottom of container.
- Slowly and evenly, pour aggregate into liquid mixture and mix until a uniform texture is obtained.

**Application**

Apply the required precoat primer: Sealer 100 (sku# 12540 EMEA) or Concrete Sealer (sku# 12560 Americas) to concrete/cement prepared surface. See Technical Data Sheets on Sealer 100 and Concrete Sealer for specific product details.

**Instructions:**

Recoat time - 1 hour

**APPLICATION:**

Spread Ultra Quartz over application area with a trowel. Spread back and forth to create top layer. To produce a smooth finish, trowel again once product has thickened (approx. 20 minutes into pot life).

**NOTES:**

- For a truly smooth finish, dip trowel in water before each application to lessen build-up on trowel and break surface tension of epoxy.
- DO NOT pour water onto uncured epoxy.

**Storage:**

Store at room temperature, 70 °F (21°C)

**Compliances:**

Approved in the U.S. for use in meat and poultry processing plants  
Accepted by Canadian Department of Agriculture Food Safety Service

**Chemical Resistance:**

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F (24°C)

Ammonia	Excellent
Chlorinated Solvent	Excellent
Hydrochloric 10%	Excellent
Kerosene	Excellent
Methanol	Very good
Sodium Hydroxide 10%	Excellent
Sulfuric 10%	Excellent
Toluene	Excellent

**Precautions:**

**FOR INDUSTRIAL USE ONLY:** Please refer to the appropriate Safety Data Sheet prior to using this product.

**Warranty:**

ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

**Order Information:**

<u>Item No.</u>	<u>Package Size</u>
13550	35 lb. (15.9 Kg)

**Contacts:**

[www.itwpp.com](http://www.itwpp.com)

ITW Performance Polymers (EMEA)  
Bay 150, Shannon Industrial Estate  
Shannon, County Clare, Ireland V14 DF82  
TEL: +353 61 771 500  
FAX: +353 61 471 285  
Email: customerservice.shannon@itwpp.com

ITW Performance Polymers (US)  
30 Endicott Street  
Danvers, MA 01923 USA  
TEL: +1-855-489-7262  
FAX: +1-978-774-0516  
Email: info@itwpp.com

**Disclaimer:**

**Product Use:** The information herein is based upon good faith testing that ITW PP believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW PP control and uniquely within users knowledge and control can affect the use and performance of an ITWPP product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsible for evaluating any ITW PP product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.

**Exclusion of Warranties:** As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW PP makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW PP shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.