



TECHNICAL DATA SHEET – DENSIT® WEARFLEX 2000 CHEMICALLY BONDED CORUNDUM-CERAMIC

Revised: v2 04/2021

DESCRIPTION

Densit® WearFlex 2000 wear resistant linings provide superior protection against heavy erosive wear at temperatures up to 400°C (750°F).

CONSUMPTION AT 25 MM

Densit® WearFlex 2000	72 kg/m ²
Densit® Anchoring mesh	1 m ² /m ²
Densit® Curing Compound	0.25 l/m ²

CONSUMPTION AT 40 MM

Densit® WearFlex 2000	115 kg/m ²
Densit® Anchoring mesh	1 m ² /m ²
Densit® Curing Compound	0.25 l/m ²

SPECIFICATION

- Install mesh
- Mix dry compound for 1 minute
- Add water and mix for 8 minutes
- Trowel mix onto mesh
- Apply Densit® Curing Compound
- For more details refer to the "Densit® WearFlex Manual"

Densit® WearFlex 2000 is a trowellable one-component ready-mix delivered in 25 kg bags.

The bags must be stored on a dry stock to maintain the good properties of the compound. The guaranteed shelf life is 14 months from production date. A paddle mixer must be used for mixing the compound. A significant change in consistency of the material (from dry to plastic) must be observed within 3 minutes from addition of water. Avoid Densit® compound to make contact with aluminium or galvanised steel. Densit® WearFlex 2000 should be installed on a standard expanded metal mesh welded on the steel casing.

TECHNICAL DATA

PROPERTIES	STANDARD	DENSIT® WEARFLEX 2000
Density - kg/m ³ (lb/ft ³)	EN 1015-6	2900 (181)
Compressive strength - MPa	EN 12190	160
Flexural strength - MPa	EN 196-1	20
Dynamic E-modul - MPa	EN 12504-4	70-80 10 ³
Casting shrinkage - vol. %		0.2
Thermal conductivity - w/m°C		1.5
Coef. of thermal expansion - 1/°C (1/°F)	EN 1770	10x10 ⁻⁶ (5.6x10 ⁻⁶)
Heat capacity - KJ/kg°C		0.9-1.0
Max. service temperature - °C (°F)		400 (750)
Abrasion resistance - cm ³ /50cm ²	DIN 52108	1 - 1.5
Erosive resistance - min/cm ³		200
Chemical composition - % CaO % SiO ₂ % Al ₂ O ₃ + TiO ₂ % Fe ₂ O ₃ % Cr ₂ O ₃	EN 196-10	18 25 55 <0.2 <0.0002
sBag size - kg		25
Bag size - kg		1250

The figures given are typical values.

Please contact ITW Performance Polymers or the nearest distributor for further information.